


This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Original) Process for the production of cross-linked polyvinyl acetals, in which a polymer (A1) is cross-linked, which, relative to its total weight, contains

- a) 1.0 to 99.9% by weight of structural units of formula (1)



in which R¹ means hydrogen or methyl,

- b) 0 to 99.0% by weight of structural units of formula (2)




in which R² represents hydrogen or an alkyl radical with 1 to 6 carbon atoms,

- c) 0 to 70.0% by weight of structural units of formula (3)



in which R³, R⁴, R⁵ and R⁶, in each case independently of one another, are radicals with a molecular weight in the range of 1 to 500 g/mol,

- d) 0.00001 to 30.0% by weight of structural units of formula (4)



(4)

in which R^7 and R^8 , in each case independently of one another, contain hydrogen, a carboxyl group, an alkyl group with 1 to 10 carbon atoms, which optionally can exhibit one or more COOH groups as substituents, or represents an optionally substituted aryl group with 6 to 12 carbon atoms, characterized in that in any sequence

- (i) Polymer (A1) is reacted with at least one polyaldehyde of formula (5),



in which R^9 represents a bond or a radical that has 1 to 40 carbon atoms, and n is an integer that is greater than or equal to 2,

and


- (ii) Groups of formula (1) and formula (4) are at least partially esterified with one another.

2. (Currently Amended) Process according to claim 1 ~~at least one of the preceding claims~~, wherein a compound (5) with $n = 2$ or 3 is used.

3. (Currently Amended) Process according to claim 1 ~~at least one of the preceding claims~~, wherein a compound (5) is used, in which R^9 is an aliphatic, cycloaliphatic and/or aromatic group with 1 to 12 carbon atoms.

4. (Currently Amended) Process according to claim 1 ~~at least one of the preceding claims~~, wherein glutaric dialdehyde and/or n -nonanedial is used as compound (5).

5. (Currently Amended) Process according to claim 1 ~~at least one of the preceding claims~~, wherein at any time, at least one compound of formula (6) is added,



(6)

in which R¹⁰ and R¹¹, in each case independently of one another, are hydrogen, an alkyl group with 1 to 10 carbon atoms or an optionally substituted aryl group with 6 to 12 carbon atoms.

6. (Original) Process according to claim 5, wherein n-butyraldehyde is used as compound (6).

7. (Currently Amended) Process according to claim 5 ~~and/or 6~~, wherein

(1) 95.00 to 99.99 parts by weight of at least one compound (6)

(2) 0.01 to 5.00 parts by weight of at least one polyaldehyde (5)

are used, whereby the indicated parts by weight are supplemented up to 100.00 parts by weight.

8. (Currently Amended) Process according to claim 1 ~~at least one of the preceding claims~~, wherein esterification (ii), optionally in the presence of at least one softener, is performed at mass temperatures in the range of 80 to 280°C.

9. (Original) Process according to claim 8, wherein the cross-linking is performed in an extruder, a kneading aggregate or another heatable aggregate.

10. (Currently Amended) Cross-linked polyvinyl acetal that can be obtained by a process according to claim 1 ~~at least one of the preceding claims~~.

11. (Original) Polyvinyl acetal according to claim 10, wherein its total content of esterified and non-esterified carboxyl groups is less than or equal to 10.0% by weight, relative to the total weight of the polyvinyl acetal.

12. (Currently Amended) Polyvinyl acetal according to claim 10 ~~and/or 11~~, wherein it contains a softener.

13. (Currently Amended) Molding compound that contains a polyvinyl acetal according to claim 10 ~~at least one of claims 10 to 12~~.

14. (Currently Amended) Film that contains a polyvinyl acetal according to claim 10 ~~at least one of claims 10 to 12~~.

15. (Original) Use of a film according to claim 14 for the production of laminated safety glasses.

16. (Currently Amended) Coating that contains a polyvinyl acetal according to claim 10 ~~at least one of claims 10 to 12~~.

17. (Currently Amended) Use of a polyvinyl acetal according to claim 10 ~~at least one of claims 10 to 12~~ for the production of ion-conductive intermediate layers for eletrochromic systems.